EUROBIT PRO

2023-07-10

Quality passport Nr. 80.100-1007

Analyze Penetration Bitumen 70/100

ASTM D 70—09

Properties	Range	Result	Test Method
Penetration Point @25°C	70-100	91.2	ASTM D 5
Softening Point °C	46-56	52.3	ASTM D 36
Ductility	100 min	104	ASTM D 113
Loss on Heating (Wt)%	0.2 max	0.2	ASTM D 6
Drop in Penetration after Heating %	20 max	18.8	ASTM D 6
Flash Point °C	250 min	263	ASTM D 92
Solubility in CS2 (Wt)% OM Insoluble in CS2 (Wt)%	99.5 min 0.5 max	99.55 0.5	ASTM D 4
Specific Gravity °C	1.01-1.06	1.014	ASTM D 70
Spot Test	Negative	Negative	AASHOT 102
Solidification temperature, °C	≤ 30	60	ASTM D 938
Density at 70 °C g/sm³	≤ 0, 942	0, 970	EN ISO 12185

Test Date: 2023-07-10

Tests foreseen:
Limited Liability Partnership "EUROBIT PRO" BIN 220940014804
050000, Republic of Kazakhstan, Almaty city, Medeu district, Kunaev Street, 41/49
Tel.: +7 776 002 05 14 **email info@eurobitumen.eu** **www.eurobitumen.eu**

Country of origin of the product: **Kazakhstan**